


LARSEN

TILING

TECHNICAL DATA SHEET

COLOURFAST 360 Silicone Sealant

PREMIUM GRADE

NEUTRAL CURE SILICONE SEALANT

LOW MODULUS

HIGHLY FLEXIBLE

SANITARY SEALANT

A premium quality, one part low modulus elastic sealant based on silicones for sanitary and construction applications. The fast curing formulation exhibits excellent adhesion to baths, basins, shower enclosures, toilets, glass, natural stone and glazed tile surrounds. After application Colourfast 360 silicone cures to provide a durable, waterproof elastic seal with low dirt pick-up and mould resistance. Colourfast 360 silicone is available in a range of colours to compliment Colourfast 360 Tile Grout.



TECHNICAL DATA SHEET

PRODUCT INFORMATION

| | |
|----------------------|---|
| FORM | Paste |
| STANDARD COLOURS: | Clear, Jasmine, Ivory, Limestone, Taupe, Walnut, Beige, Silver Grey, Grey, Anthracite, Black, White |
| HAZARD INFORMATION: | Contains biocide to protect cured sealant. Avoid contact with skin. Ensure good ventilation. If uncured sealant gets into eyes, wash out with water and consult a doctor. Safety data sheet available for professional user on request. |
| CLEANING | Clean tools, equipment, etc. using white spirit. Mechanical means are necessary when the product has set. |
| PACKAGING | 300ml cartridge |
| STORAGE INSTRUCTIONS | Store in sealed containers in dry conditions, protected from extremes of temperature |
| SHELF LIFE | 18 months in unopened manufacturers packaging |

APPLICATION INFORMATION

| | |
|--------------------------|---------------|
| MIN JOINT WIDTH: | 6mm |
| MAX JOINT WIDTH: | 25mm |
| MIN JOINT DEPTH: | 5mm |
| SKIN TIME: | >10min |
| CURE RATE: | 2mm/24hr |
| APPLICATION TEMPERATURE: | +5°C TO +40°C |

PERFORMANCE INFORMATION

| | |
|-----------------------|--|
| HARDNESS: | 20+5 Shore A |
| DENSITY: | 1-1.02 |
| TEMP RESISTANCE: | -40° to +180°C |
| ELASTIC RECOVERY: | >90% |
| MAX DISTORTION: | 25% |
| ELASTIC MODULUS 100%: | >0.4MPa |
| ELONGATION AT BREAK: | 800% |
| CLASSIFICATION: | Type F - EXT-INT-CC: CLASS 25LM Type G-CC: CLASS 25LM Type S: CLASS XS1 PW INT CC EMICODE;EC1 PLUS, ISEGA Food Contact, VD1 Fire Reaction 1 |

DIRECTIONS FOR USE

PREPARATION

Surfaces to be sealed must be clean, dry, sound and free from dust, oil or grease. Primer is not required on clean glass, ceramics and enameled surfaces.

APPLICATION

Remove cartridge tip with a sharp knife. Cut nozzle to required size and angle. Using skeleton gun, apply sealant continuously, ensuring full contact with all surfaces. Must be tooled within five minutes. Soapy water will assist finishing process. Cannot be over-painted.

RESTRICTIONS

Not recommended for aquaria, on concrete, PE, PP, Teflon, polycarbonate and bituminous or wax containing surfaces. Not recommended for direct contact with the perimeter of isolation glass or the edges of laminated safety glass.

DIRECTIONS FOR USE (continued)

RESTRICTIONS

Do not use in applications where continuous water immersion is possible. The sanitary formula should not replace regular cleaning of the joint. Excessive contamination, deposits or soap remaining will stimulate the development of fungi. Adhesion tests prior to application are recommended. It is the user's responsibility to determine suitability.