

INJECTION RESIN



Larsen Injection Resin is a low viscosity, solvent-free, epoxy resin-based crack injection system. Injection Resin is mainly used for the repair of small, fine and hairline cracks in reinforced concrete structures. It can be used in dry, wet or damp conditions (no standing water) within an application temperature range of 5°C to 30°C. It can also be used as a stabiliser for weak and friable sand/cement screeds.



VERY HIGH STRENGTH

90 N/mm²

BONDS TO DRY AND DAMP SURFACES

NON-SHRINK

TECHNICAL INFORMATION:

| PRODUCT INFORMATION | |
|------------------------------|---|
| APPEARANCE: | Fluid straw coloured liquid |
| DENSITY: | 1080 kg/m ³ |
| VISCOSITY: | 1800cps @ 5°C; 340cps @ 20°C |
| MOISTURE SENSITIVITY: | Negligible |
| APPLICATION TEMP.: | 5 – 30°C |
| COMPRESSIVE STRENGTH: | 90 N/mm ² |
| TENSILE STRENGTH: | 45 N/mm ² |
| POT LIFE: | 30°C - 10 minutes; 20°C - 20 minutes; 10°C - 1 hour; 5°C - 2 hours |
| COVERAGE: | Dependent on the nature of the surface and usage. A 1kg pack produces approx. ~0.9 L of resin |

DIRECTIONS FOR USE:

MIXING

Mix all the contents of Part A with all of the contents of Part B - thoroughly by hand or with a low speed electric drill and paddle for a minimum of 3 minutes and a maximum of 5 minutes.

TOOLS

For Mixing: Slow speed drill and mixing paddle.

For Injection Applications: Injection flanges; Polythene tube to suit flanges; Plastic cartridge sets; Wire or plugs to seal injection tube; fast-setting repair mortar for sealing the surface of the crack and fixing the injection flanges.

For Gravity Application: Paint brushes, Squeegee and Mastic.

Ancillary Tools: Gloves, goggles, knife, rags and Larsolve Thinners/Cleaner.

APPLICATION

Horizontal Cracks Filled By Gravity: Use mastic to form a dam at each side of the crack to prevent the Injection Resin running onto the surrounding floor. Simply pour the resin into the crack. Keep topping up until the crack is full and will take no more resin. For very fine crazing, repeated application by paint brush or squeegee until the substrate is saturated may suffice.

Vertical Cracks: Place injection flanges over the crack and fix with fast-setting repair mortar, 100-200mm apart. Seal the face of the crack with fast-setting repair mortar. Blow through each injection flange with compressed air to ensure an injectable system. Connect the gun to lowest flange and slowly inject resin until material appears at the next highest flange. Bend the first injection tube and seal closed with wire, or use a plug. Move up one and repeat. Continue the process until all flanges have been injected. Keep a check to ensure that resin is not escaping from some other exit point.

Stabilising Porous Screeds: Pour on mixed Injection Resin and spread around with a squeegee until the substrate can absorb no more resin. As much mixed Injection Resin should be applied as the surface will absorb without superfluous material remaining on the surface.

CLEANING

Clean tools, equipment, etc. using a suitable cleaning solvent. Mechanical means are necessary when the product has set.

STORAGE

Larsen Injection Resin should be stored in closed containers protected from extremes of temperature.

SHELF LIFE

12 months in unopened manufacturer's containers.

PACKAGING

1kg packs.