



LARSEN

FLOORING

TECHNICAL DATA SHEET

QUICKSET

20+ N/mm² IN 2 HOURS

UP TO 75mm IN SINGLE LAYER

WEARING FINISH

TRAFFIC IN 2-4 HOURS

Quickset is a blend of specially selected aggregates, cements and additives to give a very fast setting cementitious patching screed mortar with high early strength. Rapid repairs can be carried out on screeds, pavements and factory floors with minimal obstruction and downtime. Quickset can be used for other rapid setting applications, such as the bedding of manhole covers, etc. Quickset is chloride-free, sulphate resistant and non-corrosive to reinforcing steel, and generally does not require a bonding agent.



THE TILE
ASSOCIATION
EXCELLENCE IN TILING



NATIONAL
TILING
ASSOCIATION
OF IRELAND LTD



NBS Source
PARTNER

For further information, consult our Technical Department.

Belfast 028 9077 4000 Birmingham 028 9053 5409 Dublin 01 8348255

LarsenBuildingProducts.com



TECHNICAL DATA SHEET

PRODUCT INFORMATION

FORM:	Free-flowing powder
COLOUR:	Dark Grey
MAXIMUM AGGREGATE SIZE:	3.0 mm
HAZARD INFORMATION:	IRRITANT – Contains cement. Consult Safety Datasheet before use
CLEANING:	Clean tools, equipment, etc. using warm water. Mechanical means are necessary when the product has set.
PACKAGING:	25kg multi-wall paper sacks
STORAGE CONDITIONS:	Store in sealed containers in dry conditions, protected from extremes of temperature.
SHELF LIFE:	6 months in unopened manufacturer's packaging.

TECHNICAL INFORMATION

WET DENSITY:	2300 kg/m ³
BED THICKNESS:	5 – 75 mm
WORKING TIME:	15 - 20 min @ 20°C
MIX PROPORTIONS:	Up to 3.2L per 25kg
TIME TO TRAFFIC: (depending on site conditions)	Light Foot Traffic: after 2 - 4 hours Full Traffic: after 1 - 2 days Covering: after 1 - 2 days
COMPRESSIVE STRENGTH:	2hr 20MPa 4hr 25MPa 7 day 35MPa 28day 40MPa
COVERAGE:	Dependent on the nature of the surface and usage. Approx. 1 m ² /25 kg @ 10 mm bed

DIRECTIONS FOR USE

PREPARATION

The surface should be clean and free from all dust and contamination. The substrate must also be sound and coarse textured, ideally mechanically prepared, e.g. needle guns, enclosed shot blasting. It is important to pre-dampen the substrate and then remove any standing water prior to laying Quickset.

MIXING

To produce an easily applied mortar for horizontal surfaces, mix 3.2 L of water to 25 kg of Quickset. For vertical applications or if a stiffer mortar is required, mix approx. 2.8 L of water to 25 kg of Quickset. Mix the mortar with a forced action mixer or a slow speed drill and paddle. Only mix the amount of material that can be used within 15 minutes.

APPLICATION

Apply and fully compact in layers not exceeding 75 mm. Layers may be build up wet on wet. Intermediate layers, which have been allowed to harden, must be well keyed to allow good bonding of subsequent layers. Thicker layers of Quickset are possible if the mortar is bulked out with up to 30% 6-10mm aggregate. Feather edging of Quickset is not permitted.

RESTRICTIONS

All work should be carried out to current best practice and industry guidelines. Quickset will take longer to harden and set at lower temperatures and should not be used below 5°C. Addition of water in excess of the recommendations will result in a loss of early and ultimate strength. Quickset can be over-coated with most of the Larsen range of surface treatments, adhesives, screeds etc.