

TECHNICAL DATA SHEET

Version: 01 Issued: Nov 11

CENENT COLOURS



Larsen Cement Colours are concentrated powder pigments for use with any cementitious mix. They are suitable for use in coloured mortars, renders, concrete mixes, grouts and pointing. Larsen Cement Colours are supplied in easy to use resealable packs.



EASY TO USE AVAILABLE IN 4 COLOURS RE-SEALABLE PACKS



Version: 01 Issued: Nov 11

TECHNICAL INFORMATION:

| PRODUCT INFORMATION | |
|---------------------|---------------------------|
| FORM: | Powder |
| COLOUR(S): | Black, Red, Brown, Yellow |
| CHLORIDE CONTENT: | Nil (i.e. <0.2 %) |
| DOSAGE: | 2% by weight of cement |



Version: 01 Issued: Nov 11

DIRECTIONS FOR USE:

APPLICATION

Add the required amount of pigments to the dry aggregates. Allow to mix for about one minute, and then add water. Allow 1kg of pigment per 50kg cement for standard shades. Lighter colours may require the use of white cement. Test before use with Lime mortars. Treat as standard mortar or concrete with regards to curing, etc. Efflorescence is a natural phenomenon which can cause the apparent lightening of coloured cement. Efflorescence generally weathers away after about 1 year. The effects of efflorescence can be reduced by the inclusion of a waterproofer in the mix.

CLEANING

Clean tools with clean water.

STORAGE

Store in a cool, dry place in closed containers.

SHELF LIFE

12 months in unopened manufacturer's containers.

PACKAGING

0.5kg and 1kg tubs.

The information and recommendations above are given in good faith based on our current knowledge and experience of the products when properly stored, handled and applied in accordance with current best practice, national standards and our recommendations. As we have no control over site conditions or methods of application, no liability can be derived from the contents of this information sheet, or from any written recommendations, or from any other advice offered. The user of the product is solely responsible for the product's suitability for the intended application and is recommended to test the suitability prior to use. We reserve the right to change the properties of our products without notice. All orders are sold subject to our current terms of sale and delivery. With the publication of this Technical Information Sheet all previous editions are no longer valid. For further information consult our Technical Department BELFAST: 028 9077 4000 DUBLIN: 01 834 8255

www.larsenbuildingproducts.com