



ADMIXTURES

TECHNICAL DATA SHEET

Mortar Plasticiser

BS EN 934

REDUCES THE WATER REQUIREMENT

REPLACES LIME

INCREASES FROST PROTECTION

REDUCES SHRINKAGE AND CRAZING

CHLORIDE-FREE

Larsen Mortar Plasticiser is a plasticising/air-entraining admixture for site-mixed bricklaying and plastering mortars. It is manufactured from a blend of specially selected synthetic surfactants. Mortar Plasticiser improves the workability of mortar for masonry, brickwork and sand/cement rendering without the need for lime. In addition, increases the resistance of the mortar to frost by entraining air.



TECHNICAL DATA SHEET

PRODUCT INFORMATION

FORM	Liquid
COLOUR	Brown
PACKAGING	5L, 25L and 200L
STORAGE CONDITIONS	This product must be stored in closed containers protected from extremes of temperature. If the product has frozen, thaw at temperatures above +4oC and reconstitute by mechanical agitation only, before carrying out trials to ensure suitability for continued use.
SHELF LIFE	12 months in unopened manufacturer's containers

TECHNICAL INFORMATION

SPECIFIC GRAVITY	~1.01g/ml
pH	7 - 9
CHLORIDE CONTENT	< 0.1% w/w
FREEZING POINT	0°C
DOSAGE	Typically 0.5 L per 100 kg cement

Mortar Plasticiser is typically used at a rate of 0.5 L per 100kg of cement. Dosage rates to achieve the desired workability will depend on the class of mortar, ambient temperatures, sand quality and cement type. Trial mixes should be carried out to determine the optimum dosage rate. For advice, contact Larsen Technical Department. Use clean, sharp, well graded sand for mortar and render mixes. Thorough mixing of the mortar is essential. Mixing should continue until a uniform consistency is achieved.

As a guide - Mix designation, compressive strength and composition for prescribed mortars without lime:

DIRECTIONS FOR USE

DIRECTIONS FOR USE

COMPATIBILITY

Mortar Plasticiser should be dispensed into the mixer with the gauging water. It should never be added to the dry cement. It should be dispensed separately to waterproofers and other additives. Lower dosages may be required when used in conjunction with some waterproofers. Mortar Plasticiser can be used with all types of Portland Cements. Some cements or pozzolanic materials may require increased dosages.

RESTRICTIONS

The mortar should be selected by reference to the British Standard Code of Practice for Use of Masonry BS 5628. All work should be carried out to current best practice, industry guidelines and British Standards. Fresh mortar must be contained in non-porous containers or similar, and the storage containers covered with polythene to prevent drying out. Protect the materials from frost. Dampen down bricks and blocks prior to use. Sands for masonry mortars must be evaluated for their suitability before use. Sands containing a high silt content may not be suitable. Trial mixes must be carried out to ascertain optimum working dosages. Severe overdosage can cause extensive air entrainment leading to weak, crumbly mortars.

Traditional Mortar Designation	BS EN 998-2 Class	Nominal Volume Proportions	Typical Weight Proportions
		Cement : Sand	Cement %
(i)	M12	1:3	20.5-25.0
(ii)	M6	1:3-4	16.0-25.0
(iii)	M4	1:5-6	11.5-16.5
(iv)	M2	1:7-8	8.5-12.5

The information and recommendations above are given in good faith based on our current knowledge and experience of the products when properly stored, handled, and applied in accordance with current best practice, national standards, and our recommendations. As we have no control over site conditions or methods of application, no liability can be derived from the contents of this information sheet, or from any written recommendations, or from any other advice offered. The user of the product is solely responsible for the product's suitability for the intended application and is recommended to test the suitability prior to use. We reserve the right to change the properties of our products without notice. All orders are sold subject to our current terms of sale and delivery. With the publication of this Technical Information Sheet all previous editions are no longer valid.