


**LARSEN**

# FLOORING

## TECHNICAL DATA SHEET

# SLC100 Self Levelling Compound

**SINGLE PACK**

**SELF-SMOOTHING**

**PROTEIN FREE**

**SMOOTH FINISH**

**CAN BE LAID UP TO 6MM**

**30 MINS OPEN TIME**

**FOOT TRAFFIC IN 4 HOURS**



**SLC100 Self-Levelling Compound** is a 1-part cementitious smoothing underlayment. It is manufactured from a controlled blend of special sands, cements and polymers and exhibits high flow properties making it both self-levelling and smoothing. Self-Levelling Compound is suitable for levelling most common subfloors such as sand/cement screed and concrete.



**NBS Source**  
PARTNER

For further information, consult our Technical Department.

LarsenBuildingProducts.com

Belfast 028 9077 4000 Birmingham 028 9053 5409 Dublin 01 8348255



## TECHNICAL DATA SHEET

### PRODUCT INFORMATION

FORM	Granular
STANDARD COLOUR	Grey
MAX AGGREGATE SIZE	0.6mm
HAZARD INFORMATION	Irritant - Consult safety datasheet before use
CLEANING	Clean tools, equipment, etc. using warm water. Mechanical means are necessary when the product has set
PACKAGING	20kg multi-wall paper sacks
STORAGE INSTRUCTIONS	Store in sealed containers in dry conditions, protected from extremes of temperature
SHELF LIFE	6 months in unopened manufacturer's packaging

### APPLICATION INFORMATION

WATER DEMAND	3.6 - 4L per 20kg bag
APPLICATION TEMPERATURE	+5°C to +30°C
WORKING TIME	Approx. 30 minutes
BED THICKNESS	Up to 6mm
TIME TO TRAFFIC (depending on site conditions)	Light Foot Traffic - after 4-6 hours Full Traffic - after 1-2 days Covering - after 1-2 days
COVERAGE	20 kg will cover approx. 4.0m <sup>2</sup> @ 3mm

### PERFORMANCE INFORMATION

\*Typical results to BS EN 13813

SHRINKAGE*	<0.2%
SCREED STRENGTH CLASS (BS EN 13813)	CT - C16 - F4
SCREED COMPRESSIVE STRENGTH*	20 MPa
SCREED FLEXURAL STRENGTH*	4 MPa

## DIRECTIONS FOR USE

### PREPARATION

The building must be weather tight prior to the placing of any screed material: the roof; external doors and windows must be in place and closed or covered and taped to prevent draughts. All substrates must be suitable to receive the screed as per current good working practices. The substrate must be structurally sound concrete or screed and be thoroughly clean, dry and free from laitance or other contaminants which may impair adhesion. Suitable mechanical preparation of substrate may be required. Air and substrate temperatures must be greater than 5°C. Relative Humidity value of the floor must be less than 75% when moisture sensitive finishes are to be laid onto SLC100 Self-Levelling Compound.

### PRIMING

Normal concrete/screed requires priming with Acrylic primer diluted 1:1 with clean water. Particularly porous concrete/screed requires priming with Acrylic primer diluted 1:1 with clean water followed by a coat of Acrylic primer applied neat. If the relative humidity value of the floor is greater than 75%, a liquid applied DPM should be used such as Larsen One Coat DPM or Larsen Universal DPM. Refer to the relevant Technical Data Sheet for guidance on their use and application.

### MIXING

Add 3.6 - 4.0L of clean water per 20kg bag (sufficient to achieve target flow without bleed or settlement). Mix with a heavy duty drill and paddle for 1-2 minutes or with a suitable continuous mixer / pump. Excess water will cause a loss of strength.

### APPLICATION

Pour or pump the mixed product over the floor. SLC100 Self-Levelling Compound will level out to a smooth finish. Where necessary, release air bubbles with a trowel or spiked roller. This practice must be carried out within 5 - 10 minutes of application. The screed must be protected from draughts within the first 6 hours, if necessary doorways and windows should be taped up with polythene. Subsequently, ensure the room has sufficient ventilation to allow the screed to dry out. After installation protect the screed from following trades. SLC100 will accept foot traffic after 4 hours. Floor coverings can be installed after 24 - 48 hours depending on thickness of SLC100, substrate and site conditions. Should any trowel marks remain, remove with a wet trowel after 1-1½hrs.

### RESTRICTIONS

SLC100 Self-Levelling Compound is not suitable for industrial use, should not be applied to flexible surfaces and cannot be used as a final wearing surface. SLC100 is suitable for use over underfloor heating systems. Room and substrate temperatures should be above 5°C during application. SLC100 can be applied up to 6mm. For thickness of >6mm, consult Technical Department for advice.